



®

Technical and Test Institute  
for Construction Prague  
Prosecká 811/76a  
190 00 Praha  
Czech Republic  
eota@tzus.cz



Member of



www.eota.eu

## European Technical Assessment

**ETA 16/0385**  
**of 13/03/2017**

### *I General Part*

#### **Technical Assessment Body issuing the ETA:**

Technical and Test Institute for Construction Prague

**Trade name of the construction product:** LAKMA TERM MW

**Product family to which the construction product belongs:**

Product area code: 4  
External Thermal Insulation Composite Systems (ETICS) with rendering, insulation product - mineral wool (MW)

**Manufacturer:**

LAKMA SAT Sp. Z o.o.  
Frysztacka 173  
43-400 Cieszyn, Poland

**Manufacturing plant(s):**

LAKMA SAT Sp. Z o.o.  
Mała Łąka 22  
43-400 Cieszyn, Poland

LAKMA SAT Sp. Z o.o.  
Akacjowa 6  
43-400 Cieszyn, Poland

**This European Technical Assessment contains:**

39 pages including 10 Annexes which form an integral part of this assessment.

Annex No. 11 Control Plan contains confidential information and is not included in the European Technical Assessment when that assessment is publicly disseminated.

**This European Technical Assessment is issued in accordance with regulation (EU) No. 305/2011 on the basis of:**

ETAG 004, edition 2013, used as European Assessment Document (EAD)

Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and should be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full (excepted the confidential Annex(es) referred to above). However, partial reproduction may be made, with the written consent of the issuing Technical Assessment Body - Technical and Test Institute for Construction Prague. Any partial reproduction has to be identified as such.

## *II Specific part*

### **1 Technical description of the product**

#### **1.1 Definition and composition of the kit**

This product is an ETICS (External Thermal Insulation Composite System) with rendering - a kit comprising components which are factory-produced by the manufacturer or component suppliers. The ETICS manufacturer is ultimately responsible for all components of the ETICS specified in this ETA.

The ETICS kit comprises a prefabricated insulation product of mineral wool (MW) to be bonded or mechanically fixed onto a wall. The methods of fixing and the relevant components are specified in the table below. The insulation product is faced with a rendering system consisting of one or more layers (site applied), one of which contains reinforcement. The rendering system is applied directly to the insulating panels, without any air gap or disconnecting layer.

The ETICS may include special fittings (e.g. base profiles, corner profiles ...) to treat details of ETICS (connections, apertures, corners, parapets, sills ...). Assessment and performance of these components is not addressed in this ETA, however the ETICS manufacturer is responsible for adequate compatibility and performance within the ETICS when the components are delivered as a part of the kit.

#### **Composition of the ETICS**

Table No. 1

	<b>Components</b>	<b>Coverage (kg/m<sup>2</sup>)</b>	<b>Thickness (mm)</b>	
<b>Insulation products with associated methods of fixing</b>		<b>Fully bonded ETICS with or without supplementary anchors (National application documents shall be taken into account).</b>		
	<ul style="list-style-type: none"><li>• Insulation product according to EN 13162 See Annex No. 1 and 2 for insulation product characteristics for fully bonded ETICS with or without additional mechanical fixing – MW lamella (TR80 and TR100)</li></ul>	/	50 to 400	
	<ul style="list-style-type: none"><li>• Adhesives:<ul style="list-style-type: none"><li>- <b>SYNTEKOL PSW</b> (cement based powder requiring addition of water about 0.25 l/kg)</li><li>- <b>UNIWERSALNA ZAPRAWA KLEJACA</b> (cement based powder requiring addition of water about 0.25 l/kg)</li><li>- <b>SYNTEKOL Q4</b> (cement based powder requiring addition of water about 0.25 l/kg)</li></ul></li></ul>	3.0 to 6.0 (dry)	3 - 20	

	Components	Coverage (kg/m <sup>2</sup> )	Thickness (mm)
<b>Mechanically fixed ETICS with anchors and supplementary adhesive (see Cl. 3.3.5 and Annex No. 9 for possible associations MW/anchors). National application documents shall be taken into account.</b>			
<b>Insulation products with associated methods of fixing</b>	<ul style="list-style-type: none"> <li>Insulation product according to EN 13162 see Annex No. 3 to Annex No. 8 for product characteristics</li> </ul>	/	50 to 300
	<ul style="list-style-type: none"> <li>Supplementary adhesives: <ul style="list-style-type: none"> <li><b>SYNTEKOL PSW</b> (cement based powder requiring addition of water about 0.25 l/kg)</li> <li><b>UNIWERSALNA ZAPRAWA KLEJACA</b> (cement based powder requiring addition of water about 0.25 l/kg)</li> <li><b>SYNTEKOL Q4</b> (cement based powder requiring addition of water about 0.25 l/kg)</li> </ul> </li> </ul>	3.0 to 6.0 (dry)	/
	<ul style="list-style-type: none"> <li>Anchors see Annex No. 9 for individual product characteristics. In addition to the following list, other anchors can be used provided that they comply with the requirements introduced in the Annex No. 9.</li> </ul>		
	- <b>Ejotherm STR U, STR U 2G</b> plastic screwed-in anchors	ETA-04/0023	
	- <b>EJOT SDM-T plus</b> plastic screwed-in anchors	ETA-04/0064	
	- <b>Ejot H1 eco</b> plastic nailed-in anchors	ETA-11/0192	
	- <b>BRAVOLL PTH-KZ 60/8-La</b> plastic nailed-in anchors	ETA-05/0055	
	- <b>BRAVOLL PTH-S 60/8-La</b> plastic screwed-in anchors	ETA-08/0267	
	- <b>BRAVOLL PTH-EX</b> plastic nailed-in anchors	ETA-13/0951	
	- <b>KEW TSD 8</b> plastic nailed-in anchors	ETA-04/0030	
	- <b>KEW TSD-V</b> plastic nailed-in anchors	ETA 08/0315	
	- <b>KEW TSDL-V</b> plastic nailed-in anchors	ETA 12/0148	
	- <b>KOELNER TFIX-8M</b> plastic nailed-in anchors	ETA-07/0336	
	- <b>KOELNER KI-10M</b> plastic nailed-in anchors	ETA-07/0291	
	- <b>KOELNER KI-10N</b> plastic nailed-in anchors	ETA-07/0221	
	- <b>KOELNER KI-10NS</b> plastic screw-in anchors	ETA-07/0221	

Components	Coverage (kg/m <sup>2</sup> )	Thickness (mm)
<ul style="list-style-type: none"> <li>- <b>KOELNER TFIIX-8S, TFIIX-8ST</b> plastic screwed-in anchors</li> <li>- <b>KOELNER TFIIX-8P</b> plastic nailed-in anchors</li> <li>- <b>Hilti SX-FV</b> plastic screwed-in anchors</li> <li>- <b>Hilti XI-FV</b> plastic gun-nailed anchors</li> <li>- <b>Hilti D-FV, D-FV T</b> plastic screwed-in anchors</li> <li>- <b>Hilti HTS-P</b> plastic screwed-in anchors</li> <li>- <b>fischer TERMOZ 8 SV</b> plastic screwed-in anchors</li> <li>- <b>fischer TERMOFIX CF 8</b> plastic nailed-in anchors</li> <li>- <b>fischer TERMOZ 8U</b> plastic screwed-in anchors</li> <li>- <b>fischer TERMOZ 8N, 8 NZ</b> plastic nailed-in anchors</li> <li>- <b>fischer TERMOZ CS 8</b> plastic screwed-in anchors</li> <li>- <b>Wkret-met LMX 10</b> plastic nailed-in anchors</li> <li>- <b>Wkret-met LMX 8</b> plastic nailed-in anchors</li> <li>- <b>Wkret-met LFM 10</b> plastic nailed-in anchors</li> <li>- <b>Wkret-met LFM 8</b> plastic nailed-in anchors</li> <li>- <b>Wkret-met WKTERM Ø 8</b> plastic nailed-in anchors</li> <li>- <b>Wkret-met eco drive</b> plastic screw-in anchors</li> <li>- <b>Wkret-met WKTERM S</b> plastic screw-in anchors</li> <li>- <b>AMEX LDK</b> plastic nailed-in anchors</li> </ul>	<ul style="list-style-type: none"> <li>ETA-11/0144</li> <li>ETA-13/0845</li> <li>ETA-03/0005</li> <li>ETA-03/0004</li> <li>ETA-05/0039</li> <li>ETA-14/0400</li> <li>ETA-06/0180</li> <li>ETA-07/0287</li> <li>ETA-02/0019</li> <li>ETA-03/0019</li> <li>ETA-14/0372</li> <li>ETA-08/0172</li> <li>ETA-09/0001</li> <li>ETA-06/0105</li> <li>ETA-06/0080</li> <li>ETA-11/0232</li> <li>ETA-13/0107</li> <li>ETA-13/0724</li> <li>ETA 09/0181</li> </ul>	

	<b>Components</b>	<b>Coverage (kg/m<sup>2</sup>)</b>	<b>Thickness (mm)</b>
<b>Base coat</b>	<ul style="list-style-type: none"> <li>- <b>SYNTEKOL PSW</b> (cement based powder requiring addition of water about 0.25 l/kg)</li> <li>- <b>UNIWERSALNA ZAPRAWA KLEJACA</b> (cement based powder requiring addition of water about 0.25 l/kg)</li> <li>- <b>SYNTEKOL Q4</b> (cement based powder requiring addition of water about 0.25 l/kg)</li> </ul>	3.0 to 6.0 (dry)	3 - 6
<b>Reinforcement</b>	<ul style="list-style-type: none"> <li>• Standard mesh applied in single layer, see Annex No. 10 for product characteristics:</li> <li>- <b>R 117 A101</b></li> <li>- <b>R 131 A101</b></li> <li>- <b>SSA-1363-145</b></li> <li>- <b>SSA-1363-160</b></li> <li>- <b>LIFITEX PRO 145</b></li> <li>- <b>LIFITEX PRO 165</b></li> <li>- <b>AKE 145</b></li> <li>- <b>AKE 170/160</b></li> <li>- <b>Asglatex 03-43</b></li> <li>- <b>Halico A 150</b></li> <li>- <b>OPTIMA NET 150</b></li> <li>- <b>OPTIMA NET 170</b></li> <li>- <b>LAKMA TERM A 150</b></li> <li>- <b>MASTERNET CLASSIC 145</b></li> </ul>	Mas per unit area < 0.4 kg/m <sup>2</sup>	< 0.5
<b>Key coat</b>	<ul style="list-style-type: none"> <li>- <b>TOTALGRUNT</b> (ready to used liquid)</li> <li>- <b>TYNKSILGRUNT</b> (ready to used liquid)</li> <li>- <b>TYNKSILGRUNT Q</b> (ready to used liquid)</li> <li>- <b>AKRYL P</b> (ready to used liquid)</li> <li>- <b>PREPARAT GRUNTUJĄCY FRANCESCO GUARDI</b> (ready to used liquid)</li> </ul>	0.20 – 0.35	/
<b>Finishing coats</b>	<ul style="list-style-type: none"> <li>• cement based powder requiring addition of water – about 0.23 l/kg: <ul style="list-style-type: none"> <li>- <b>MINERALTYNK Q Z</b> ribbed structure (max. particle size 1.5; 2.0; 2.5; 3.0 mm)</li> <li>- <b>MINERALTYNK Q K</b> floated structure (max. particle size 1.5; 2.0; 2.5; 3.0 mm)</li> <li>- <b>POROLIT QM</b></li> </ul> </li> </ul>	1.3 – 4.5 regulated by max. particle size	Regulated by particle size

Components	Coverage (kg/m <sup>2</sup> )	Thickness (mm)
<p>machine applied (max. particle size 1.5; 2.0 mm)</p> <p>Mineral finishing coats can be used in combination with a decorative coat SILMAL ST, SILMAL SN, SILMAL SN REPAIR, AKRYL FASADA, FASMAL</p>		
<ul style="list-style-type: none"> <li>• Ready to use paste – binder based on colloidal silica: <ul style="list-style-type: none"> <li>- <b>TYNKSIL S Z</b> ribbed structure (max. particle size 1.5; 2.0; 2.5; 3.0 mm)</li> <li>- <b>TYNKSIL S K</b> floated structure (max. particle size 1.5; 2.0; 2.5; 3.0 mm)</li> <li>- <b>POROLIT S</b> machine applied (max. particle size 1.5; 2.0 mm)</li> </ul> </li> </ul> <p>Finishing coats based on colloidal silica can be used in combination with a decorative coat SILMAL ST, SILMAL SN, SILMAL SN REPAIR, AKRYL FASADA, FASMAL</p>	1.2 – 3.8 regulated by max. particle size	Regulated by particle size
<ul style="list-style-type: none"> <li>• Ready to use paste – silicone binder: <ul style="list-style-type: none"> <li>- <b>TYNKSIL QS Z</b> ribbed structure (max. particle size 1.5; 2.0; 2.5; 3.0 mm)</li> <li>- <b>TYNKSIL QS K</b> floated structure (max. particle size 1.5; 2.0; 2.5; 3.0 mm)</li> <li>- <b>POROLIT QS</b> machine applied (max. particle size 1.5; 2.0 mm)</li> </ul> </li> </ul> <p>Silicone finishing coats can be used in combination with a decorative coat SILMAL ST, SILMAL SN, SILMAL SN REPAIR, AKRYL FASADA, FASMAL</p>	1.2 – 3.8 regulated by max. particle size	Regulated by particle size
<ul style="list-style-type: none"> <li>• Ready to use paste – silicate binder: <ul style="list-style-type: none"> <li>- <b>TYNKSIL Z</b> ribbed structure (max. particle size 1.5; 2.0; 2.5; 3.0 mm)</li> <li>- <b>TYNKSIL K</b> floated structure (max. particle size 1.5; 2.0; 2.5; 3.0 mm)</li> </ul> </li> </ul> <p>Silicate finishing coats can be used in combination with a decorative coat SILMAL ST, SILMAL SN, SILMAL SN REPAIR, AKRYL FASADA, FASMAL</p>	2.0 – 3.8 regulated by max. particle size	Regulated by particle size
<ul style="list-style-type: none"> <li>• Ready to use paste – acrylic binder: <ul style="list-style-type: none"> <li>- <b>AKRYLTYNK Z</b> ribbed structure (max. particle size 1.5; 2.0; 2.5; 3.0 mm)</li> </ul> </li> </ul>	1.2 – 3.8 regulated by max. particle size	Regulated by particle size

	<b>Components</b>	<b>Coverage (kg/m<sup>2</sup>)</b>	<b>Thickness (mm)</b>
	<ul style="list-style-type: none"> <li>- <b>AKRYLTYNK K</b> floated structure (max. particle size 1.5; 2.0; 2.5; 3.0 mm)</li> <li><b>POROLIT Z</b> machine applied (max. particle size 1.5; 2.0 mm)</li> </ul> <p>Acrylic finishing coats can be used in combination with a decorative coat SILMAL ST, SILMAL SN, SILMAL SN REPAIR, AKRYL FASADA, FASMAL</p>		
	<ul style="list-style-type: none"> <li>• Mosaic finishing coats, ready to use paste – acrylic binder:           <ul style="list-style-type: none"> <li>- <b>AKRYLTYNK M</b> ribbed structure (max. particle size 1.6 mm)</li> <li>- <b>TYNK KWARCOWY</b> ribbed structure manually and machine applied (max. particle size 1.6 mm)</li> <li>- <b>TYNK MARMUROWY</b> ribbed structure manually and machine applied (max. particle size 1.6 mm)</li> </ul> </li> </ul> <p>Mosaic finishing coats can be used in combination with decorative coat IMPREGNAT DO TYNKÓW MOZAIKOWYCH</p>	1.8 – 6.0	Regulated by particle size
<b>Decorative coats</b>	<b>SILMAL SN</b> ready to use liquid based on silicone binder <b>SILMAL SN REPAIR</b> ready to use liquid based on silicone binder <b>AKRYL FASADE</b> ready to use liquid based on acrylic binder <b>SILMAL ST</b> ready to use liquid based on silicate binder <b>FASMAL</b> ready to use liquid based on acrylic binder <b>TYNKSIL QS Z Repair</b> ready to used paste based on silicone binder, max. particle size 0.5 mm <b>AKRYLTYNK Z Renowacyjny</b> ready to used paste based on acrylic binder, max. particle size 0.5 mm <b>IMPREGNAT DO TYNKÓW MOZAIKOWYCH</b> ready to use liquid based on acrylic binder		
<b>Ancillary materials</b>	Remain under the manufacturer's responsibility		

## **2 Specification of the intended use(s) in accordance with the applicable European Assessment Document (hereinafter "EAD")**

### **2.1 Intended use**

This ETICS is intended for use as external insulation of buildings' walls. The walls are made of masonry (bricks, blocks, stones ...) or concrete (cast on site or as prefabricated panels). The characteristics of the walls shall be verified prior to use of the ETICS, especially regarding conditions for reaction to fire classification and for fixing of the ETICS either by bonding or mechanically. The ETICS is designed to give the wall to which it is applied satisfactory thermal insulation.

The ETICS is made of non load-bearing construction elements. It does not contribute directly to the stability of the wall on which it is installed, but it can contribute to durability by providing enhanced protection from the effect of weathering.

The ETICS can be used on new or existing (retrofit) vertical walls. It can also be used on horizontal or inclined surfaces which are not exposed to precipitation.

The ETICS is not intended to ensure the airtightness of the building structure.

The choice of the method of fixing depends on the characteristics of the substrate, which may need preparation (see cl. 7.2.1 of the ETAG 004) and shall be done in accordance with the national instructions.

The ETICS belong to Category S/W2, according to EOTA Technical Report No 034.

### **2.2 Manufacturing**

The European Technical Assessment is issued for the ETICS on the basis of agreed data/information, deposited with the Technical and Test Institute Prague, which identifies the ETICS that has been assessed and judged.

### **2.3 Design and installation**

The installation instructions including special installation techniques and provisions for the qualification of the personnel are given in the manufacturer's technical documentation.

Design, installation and execution of ETICS are to be in conformity with national documents. Such documents and the level of their implementation in Member States' legislation are different. Therefore, the assessment and declaration if performance are done taking into account general assumptions introduced in the chapters 7.1 and 7.2 of ETAG 004 used as EAD, which summarize how information introduced in the ETA and related documents is intended to be used in the construction process and gives advice to all parties interested when normative documents are missing.

### **2.4 Packaging, transport and storage**

The information on packaging, transport and storage is given in the manufacturer's technical documentation. It is the responsibility of the manufacturer(s) to ensure that this information is made known to the concerned people.

## **2.5        Use, maintenance and repair**

The provisions made in this European Technical Assessment are based on an assumed working life of the ETICS of at least 25 years, provided that the requirements for the packaging, transport, storage, installation as well as appropriate use, maintenance and repair are met. The indication given on the working life cannot be interpreted as a guarantee given by the manufacturer or the Technical Assessment Body, but should only be regarded as a means for choosing the appropriate products in relation to the expected, economically reasonable working life of the works.

The finishing coat shall normally be maintained in order to fully preserve the ETICS performance. Maintenance includes at least:

- visual inspection of the ETICS,
- repairing of localized damaged areas due to accidents,
- the aspect maintenance with products adapted and compatible with the ETICS (possibly after washing or ad hoc preparation).

Necessary repairs should be performed as soon as the need has been identified.

It is important to be able to carry out maintenance as far as possible using readily available products and equipment, without spoiling appearance. Only products which are compatible with the ETICS shall be used.

The information on use, maintenance and repair is given in the manufacturer's technical documentation. It is the responsibility of the manufacturer(s) to ensure that this information is made known to the concerned people.

### **3 Performance of the product and references to the methods used for its assessment**

The performances of the kit as described in this chapter are valid provided that the components of the kit comply with Annexes 1 - 8.

#### **3.1 Safety in case of fire (BWR 2)**

##### **3.1.1 Reaction to fire (ETAG 004 - clause 5.1.2.1, EN 13501-1)**

Table No. 2

Configuration	Organic content / heat of combustion	Flame retardant content	Euroclass according to EN 13501-1
Adhesive	- / max 0.36 MJ/kg	No flame retardant	A2 – s1, d0
Panels of mineral wool (MW) Maximal density of 160 kg/m <sup>3</sup>	In quantity ensuring Euroclass A1 according to 13501-1	-	
Base coat	- / max 0.36 MJ/kg	No flame retardant	
Glass fibre mesh	- / max 8.17 MJ/kg	No flame retardant	
Key coat	- / max. 5.82 MJ/kg	No flame retardant	
Finishing coats including decorative coats for mineral finishing coating	- / max 2.51 MJ/kg	No flame retardant	

Note: A European reference fire scenario has not been laid down for facades. In some Member States, the classification of ETICS according to EN 13501-1 might not be sufficient for the use in facades. An additional assessment of ETICS according to national provisions (e.g. on the basis of a large scale test) might be necessary to comply with Member State regulations, until the existing European classification system has been completed.

### 3.2 Hygiene, health and environment (BWR 3)

#### 3.2.1 Water absorption (ETAG 004 - clause 5.1.3.1)

- Base coat **SYNTEKOL PSW/ UNIWERSALNA ZAPRAWA KLEJACA/ SYNTEKOL Q4:**

Water absorption after 1 hour < 1 kg/m<sup>2</sup>

Water absorption after 24 hours < 0.5 kg/m<sup>2</sup>

- Rendering system:

Table No. 3

	Water absorption after 24 hours	
	< 0.5 kg/m <sup>2</sup>	≥ 0.5 kg/m <sup>2</sup>
<b>Rendering system:</b> base coat <b>SYNTEKOL PSW/ UNIWERSALNA ZAPRAWA KLEJACA/ SYNTEKOL Q4</b> + finishing coats as indicated here:	<b>MINERALTYNK Q Z MINERALTYNK Q K</b>	X
	<b>POROLIT QM</b>	X
	<b>TYNKSIL S Z TYNKSIL S K</b>	X
	<b>POROLIT S</b>	X
	<b>TYNKSIL QS Z TYNKSIL QS K</b>	X
	<b>POROLIT QS</b>	X
	<b>TYNKSIL Z TYNKSIL K</b>	X
	<b>AKRYLTYNK Z AKRYLTYNK K</b>	X
	<b>POROLIT Z</b>	X
	<b>AKRYLTYNK M</b>	X
	<b>TYNK KWARCOWY</b>	X
	<b>TYNK MARMUROWY</b>	X

### **3.2.2 Watertightness (ETAG 004 - clause 5.1.3.2)**

#### **3.2.2.1 Hygrothermal behaviour**

Pass (without defects).

#### **3.2.2.2 Freeze–thaw behaviour**

Freeze-thaw resistant - according to the water absorption test result.

### **3.2.3 Impact resistance (ETAG 004 - clause 5.1.3.3)**

Table No. 4

<b>Render coating:</b> base coat <b>SYNTEKOL PSW/ UNIWERSALNA ZAPRAWA KLEJACA/ SYNTEKOL Q4</b> + reinforcement and finishing coats listed hereafter:	<b>Single standard mesh</b>
<b>MINERALTYNK Q Z</b>	Category I
<b>MINERALTYNK Q K</b>	Category I
<b>POROLIT QM</b>	Category I
<b>TYNKSIL S Z</b>	Category I
<b>TYNKSIL S K</b>	Category I
<b>POROLIT S</b>	Category I
<b>TYNKSIL QS Z</b>	Category I
<b>TYNKSIL QS K</b>	Category I
<b>POROLIT QS</b>	Category I
<b>TYNKSIL Z</b>	Category I
<b>TYNKSIL K</b>	Category I
<b>AKRYLTYNK Z</b>	Category I
<b>AKRYLTYNK K</b>	Category I
<b>POROLIT Z</b>	Category I
<b>AKRYLTYNK M</b>	Category I
<b>TYNK KWARCOWY</b>	Category I
<b>TYNK MARMUROWY</b>	Category I

### 3.2.4 Water vapour permeability (ETAG 004 - clause 5.1.3.4)

Table No. 5

Rendering system: base coat <b>SYNTEKOL PSW/ UNIWERSALNA ZAPRAWA KLEJACA/ SYNTEKOL Q4</b> + reinforcement and finishing coats indicated hereafter	Equivalent air layer thickness $s_d$
	<b>Single standard mesh</b>
<b>MINERALTYNK Q Z MINERALTYNK Q K</b>	$\leq 0.26$ m
<b>POROLIT QM</b>	$\leq 0.26$ m
<b>TYNKSIL S Z TYNKSIL S K</b>	$\leq 0.32$ m
<b>POROLIT S</b>	$\leq 0.32$ m
<b>TYNKSIL QS Z TYNKSIL QS K</b>	$\leq 0.45$ m
<b>POROLIT QS</b>	$\leq 0.45$ m
<b>TYNKSIL QS Z + SILMAL SN</b>	$\leq 0.45$ m
<b>TYNKSIL QS K + SILMAL SN</b>	$\leq 0.45$ m
<b>POROLIT QS + SILMAL SN</b>	$\leq 0.45$ m
<b>TYNKSIL QS Z + SILMAL ST</b>	$\leq 0.53$ m
<b>TYNKSIL QS K + SILMAL ST</b>	$\leq 0.53$ m
<b>POROLIT QS + SILMAL ST</b>	$\leq 0.53$ m
<b>TYNKSIL QS Z + FASMAL</b>	$\leq 0.53$ m
<b>TYNKSIL QS K + FASMAL</b>	$\leq 0.53$ m
<b>POROLIT QS + FASMAL</b>	$\leq 0.53$ m
<b>TYNKSIL Z TYNKSIL K</b>	$\leq 0.46$ m
<b>TYNKSIL Z + SILMAL SN</b>	$\leq 0.50$ m
<b>TYNKSIL K + SILMAL SN</b>	$\leq 0.50$ m
<b>TYNKSIL Z + SILMAL ST</b>	$\leq 0.46$ m
<b>TYNKSIL K + SILMAL ST</b>	$\leq 0.46$ m
<b>TYNKSIL Z + FASMAL</b>	$\leq 0.67$ m
<b>TYNKSIL K + FASMAL</b>	$\leq 0.67$ m
<b>AKRYLTYNK Z AKRYLTYNK K</b>	$\leq 0.46$ m

<b>POROLIT Z</b>	≤ 0.46 m
<b>AKRYLTYNK Z + SILMAL SN</b>	≤ 0.46 m
<b>AKRYLTYNK K + SILMAL SN</b>	≤ 0.46 m
<b>POROLIT Z + SILMAL SN</b>	≤ 0.46 m
<b>AKRYLTYNK Z + SILMAL ST</b>	≤ 0.46 m
<b>AKRYLTYNK K + SILMAL ST</b>	≤ 0.46 m
<b>POROLIT Z + SILMAL ST</b>	≤ 0.46 m
<b>AKRYLTYNK Z + FASMAL</b>	≤ 0.46 m
<b>AKRYLTYNK K + FASMAL</b>	≤ 0.46 m
<b>POROLIT Z + FASMAL</b>	≤ 0.46 m
<b>AKRYLTYNK M</b>	≤ 0.44 m
<b>TYNK KWARCOWY</b>	≤ 0.44 m
<b>TYNK MARMUROWY</b>	≤ 0.44 m
<b>AKRYLTINK M + IMPREGNANT DO TYNKOW ŻYWICNYCH</b>	≤ 0.44 m
<b>TYNK MARMUROWY + IMPREGNANT DO TYNKOW ŻYWICNYCH</b>	≤ 0.44 m
<b>TYNK KWARCOWY + IMPREGNANT DO TYNKOW ŻYWICNYCH</b>	≤ 0.44 m

### **3.2.5      Release of dangerous substances (ETAG 004 - clause 5.1.3.5, EOTA TR034)**

The kit was not assessed according EOTA TR 34.

### **3.3           Safety and accessibility in use (BWR 4)**

#### **3.3.1       Bond strength between base coat and insulation product (ETAG 004 - clause 5.1.4.1.1)**

Base Coat **SYNTEKOL PSW/ UNIWERSALNA ZAPRAWA KLEJACA/ SYNTEKOL Q4:**

- Initial state: bond strength  $\geq 0.012$  MPa but a cohesive failure in the insulation product
- After hygrothermal cycles: bond strength  $\geq 0.004$  MPa but a cohesive failure in the insulation product
- After freeze-thaw cycles: test not required (see Cl. 3.2.2.2 of this ETA)

#### **3.3.2       Bond strength between adhesive and substrate / insulation product (ETAG 004 - clauses 5.1.4.1.2, 5.1.4.1.3)**

Table No. 6

		Initial state	48 hours immersion in water + 2 hours. 23°C/50% RH	48 hours immersion in water + 7 days 23°C/50% RH
<b>SYNTEKOL PSW / UNIWERSALNA ZAPRAWA KLEJACA / SYNTEKOL Q4</b>	Concrete	$\geq 0.25$ MPa	$\geq 0.08$ MPa	$\geq 0.25$ MPa
	MW lamella	$\geq 0.08$ MPa	$\geq 0.03$ MPa	$\geq 0.08$ MPa
	MW board	< 0.08 MPa Failure in thermal insulation product	< 0.03 MPa Failure in thermal insulation product	< 0.08 MPa Failure in thermal insulation product

### 3.3.3 Bond strength after ageing (ETAG 004 - clause 5.1.7.1)

Base Coat **SYNTEKOL PSW/ UNIWERSALNA ZAPRAWA KLEJACA/ SYNTEKOL Q4:**

- After ageing: bond strength  $\geq 0.017$  MPa but a cohesive failure in the insulation product
- After freeze-thaw cycles After freeze-thaw cycles: test not required (see Cl. 3.2.2.2 of this ETA)

### 3.3.4 Fixing strength (ETAG 004 - clause 5.1.4.2)

Test not required (no limitation of ETICS length).

### 3.3.5 Wind load resistance (ETAG 004 - clause 5.1.4.3)

- Insulation product - MW board (TR15)

Table No. 7

Anchor description	Trade name		See Annex No. 9	
	Assembly		Surface assembly	Countersunk assembly (only monodensity products)
	Plate diameter (mm)		60 or more	
MW board characteristics (TR15)	Thickness (mm)		≥ 50	≥ 100
	Tensile strength (kPa)		≥ 15	
Maximal load	Anchors placed at the body of the insulation product	R <sub>panel</sub> in dry condition	min. value: 0.44 kN average value: 0.49 kN	
		R <sub>panel</sub> in wet condition	min. value: 0.32 kN average value: 0.34 kN	
	Anchors placed at joints of the insulation product	R <sub>joint</sub> in dry condition	min. value: 0.41 kN average value: 0.42 kN	
		R <sub>joint</sub> in wet condition	min. value: 0.24 kN average value: 0.26 kN	

- **Insulation product - MW board (TR10, monodensity)**

Table No. 8

Anchor description	Trade name	See Annex No. 9			
		plate stiffness $\geq 0.3$		plate stiffness $\geq 0.5$	
	Assembly method	Surface	Countersunk	Surface	Countersunk
Plate diameter (mm)		60 or more			
<b>MW board characteristics (TR10, monodensity)</b>	Thickness (mm)	$\geq 60$	$\geq 100$	$\geq 50$	$\geq 100$
	Tensile strength (kPa)	$\geq 10$			
Maximal load	Anchors placed at the body of the insulation product	$R_{panel}$ in dry conditions	min. value: 0.37 kN mean value: 0.39 kN	min. value: 0.48 kN mean value: 0.55 kN	
		$R_{panel}$ in wet conditions	min. value: 0.19 kN mean value: 0.22 kN	No performance assessed	
	Anchors placed at joints of the insulation product	$R_{joint}$ in dry conditions	min. value: 0.27 kN mean value: 0.32 kN	min. value: 0.39 kN mean value: 0.43 kN	
		$R_{joint}$ in wet conditions	min. value: 0.18 kN mean value: 0.19 kN	No performance assessed	

- **Insulation product - MW board (TR10, dualdensity)**

Table No. 9

<b>Anchor description</b>	Trade name		<b>Anchors BRAVOLL PTH 60/8 with plate IT PTH 100</b>	<b>Anchors BRAVOLL PTH 60/8 with plate IT PTH 140</b>	<b>Koelner TFIK-8 S with plate Koelner KWL 090</b>
	Assembly		Surface	Surface	Surface
	Plate diameter (mm)		100	140	90
<b>MW board (TR10, dual density)</b>	Thickness (mm)		≥ 100	≥ 100	≥ 80
	Tensile strength (kPa)		≥ 10		
<b>Maximal load</b>	Anchors placed at the body of the insulation product	R <sub>panel</sub> in dry condition	min. value: 0.61 kN average value: 0.69 kN	min. value: 0.80 kN average value: 0.83 kN	min. value: 0.54 kN average value: 0.56 kN
		R <sub>panel</sub> in wet condition	No performance assessed	No performance assessed	No performance assessed
	Anchors placed at joints of the insulation product	R <sub>joint</sub> in dry condition	min. value: 0.44 kN average value: 0.57 kN	min. value: 0.56 kN average value: 0.62 kN	min. value: 0.47 kN average value: 0.49 kN
		R <sub>joint</sub> in wet condition	No performance assessed	No performance assessed	No performance assessed

Table No. 10

Anchor description	Trade name	Anchors ejotherm STR U 2G with additional plate VT 90 + 2G	Anchors BRAVOLL PTH-60/8 with additional plate ZT 100	Anchors Wkret-met eco-drive W	Anchors fischer termoz SV II ecotwist
		Assembly	Countersunk		Special
	Plate diameter (mm)	112.5	100	110	60
<b>characteristics</b> <b>MW board</b> <b>(TR10, dual density)</b>	Thickness (mm)	$\geq 100$			
	Tensile strength (kPa)	$\geq 10$			
Maximal load	Anchors placed at the body of the insulation product	R <sub>panel</sub> in dry condition	min. value: 0.78 kN average value: 0.91 kN	min. value: 0.63 kN average value: 0.72 kN	min. value: 0.63 kN average value: 0.65 kN
		R <sub>panel</sub> in wet condition	No performance assessed		
Maximal load	Anchors placed at joints of the insulation product	R <sub>joint</sub> in dry condition	min. value: 0.60 kN average value: 0.70 kN	min. value: 0.58 kN average value: 0.65 kN	min. value: 0.47 kN average value: 0.51 kN
		R <sub>joint</sub> in wet condition	No performance assessed		

Table No. 11

Anchor description	Trade name	See Annex No. 9	
		plate stiffness $\geq 0.3$	plate stiffness $\geq 0.6$
	Assembly method	Surface assembly	
MW board characteristics (TR10, dual density)	Plate diameter (mm)	60 or more	
	Thickness (mm)	$\geq 80$	$\geq 100$
Maximal load	Tensile strength (kPa)	$\geq 10$	
	Anchors placed at the body of the insulation product	$R_{\text{panel}}$ in dry conditions	min. value: 0.38 kN mean value: 0.41 kN
		$R_{\text{panel}}$ in wet conditions	No performance assessed
	Anchors placed at joints of the insulation product	$R_{\text{joint}}$ in dry conditions	min. value: 0.32 kN mean value: 0.37 kN
		$R_{\text{joint}}$ in wet conditions	No performance assessed

Table No. 12

<b>Anchor description</b>	Trade name		<b>Anchors BRAVOLL PTH KZ/S with plate IT PTH 100</b>	<b>Anchors BRAVOLL PTH KZ/S with plate IT PTH 140</b>
	Assembly		Surface	Surface
	Plate diameter (mm)		100	140
<b>MW board (TR10, dual density)</b>	Thickness (mm)		$\geq 100$	$\geq 100$
	Tensile strength (kPa)		$\geq 10$	
<b>Maximal load</b>	Anchors placed at the body of the insulation product	$R_{panel}$ in dry condition	min. value: 0.67 kN average value: 0.69 kN	min. value: 0.78 kN average value: 0.84 kN
		$R_{panel}$ in wet condition	No performance assessed	
	Anchors placed at joints of the insulation product	$R_{joint}$ in dry condition	min. value: 0.45 kN average value: 0.54 kN	min. value: 0.60 kN average value: 0.71 kN
		$R_{joint}$ in wet condition	No performance assessed	

Table No. 13

<b>Anchor description</b>	Trade name		<b>BRAVOLL PTH-S + BRAVOLL ZT 100</b>	<b>BRAVOLL PTH-S + BRAVOLL ZP</b>	<b>Klimas Wkret-met screw-in plug eco-drive W</b>
	Assembly		Countersunk		
	Plate diameter (mm)		100	65	110
<b>MW board characteristics (TR10, monodensity)</b>	Thickness (mm)		$\geq 100$		
	Tensile strength (kPa)		$\geq 10$		
Maximal load	Anchors placed at the body of the insulation product	$R_{panel}$ in dry condition	min. value: 0.68 kN average value: 0.73 kN	min. value: 0.29 kN average value: 0.32 kN	min. value: 1.29 kN average value: 1.34 kN
Maximal load	Anchors placed at the body of the insulation product	$R_{panel}$ in wet condition	No performance assessed		
	Anchors placed at joints of the insulation product	$R_{joint}$ in dry condition	min. value: 0.57 kN average value: 0.64 kN	min. value: 0.31 kN average value: 0.36 kN	min. value: 0.83 kN average value: 0.96 kN
		$R_{joint}$ in wet condition	No performance assessed		

### 3.3.6 Render strip tensile test

- Base coat **SYNTEKOL PSW/ UNIVERSALNA ZAPRAWA KLEJACA/ SYNTekol Q4**

No performance assessed for glass fibre meshes **R 131 A101, SSA-1363-145, SSA-1363-160, LIFITEX PRO 145, LIFITEX PRO 165, AKE 145, AKE 170/160, Asglatex 03-43, Halico A 150, OPTIMA-NET 150, OPTIMA-NET 170, LAKMA TERM A 150, MASTERNET CLASSIC 145.**

Table No. 14

		Glass fibre mesh <b>R 117 A101</b> (manufacturer: SAINT-GOBAIN ADFORS CZ s.r.o.)					
		Crack width $W_{typ}$ [mm]/ number of cracks at relative elongation $\epsilon$					
Load direction		$\epsilon = 0.3\%$	$\epsilon = 0.5\%$	$\epsilon = 0.8\%$	$\epsilon = 1.0\%$	$\epsilon = 1.5\%$	$\epsilon = 2.0\%$
Warp	Sample No. 1	$\leq 0.05/10$	$\leq 0.05/17$	$\leq 0.05/32$ $\leq 0.10/1$	$\leq 0.05/52$ $\leq 0.10/4$	$\leq 0.05/63$ $\leq 0.10/15$	$\leq 0.05/70$ $\leq 0.10/17$ $\leq 0.15/3$
	Sample No. 2	$\leq 0.05/8$	$\leq 0.05/19$	$\leq 0.05/32$ $\leq 0.10/1$	$\leq 0.05/43$ $\leq 0.10/1$	$\leq 0.05/69$ $\leq 0.10/12$ $\leq 0.15/1$	$\leq 0.05/67$ $\leq 0.10/27$ $\leq 0.15/3$
	Sample No. 3	$\leq 0.05/7$	$\leq 0.05/21$	$\leq 0.05/48$	$\leq 0.05/67$ $\leq 0.10/3$	$\leq 0.05/69$ $\leq 0.10/13$	$\leq 0.05/60$ $\leq 0.10/24$ $\leq 0.15/4$
Weft	Sample No. 1	$\leq 0.05/1$	$\leq 0.05/28$	$\leq 0.05/53$	$\leq 0.05/59$ $\leq 0.10/3$	$\leq 0.05/72$ $\leq 0.10/12$	$\leq 0.05/66$ $\leq 0.10/26$
	Sample No. 2	$\leq 0.05/5$	$\leq 0.05/25$	$\leq 0.05/49$	$\leq 0.05/65$ $\leq 0.10/7$	$\leq 0.05/76$ $\leq 0.10/15$	$\leq 0.05/63$ $\leq 0.10/36$
	Sample No. 3	$\leq 0.05/8$	$\leq 0.05/16$	$\leq 0.05/42$ $\leq 0.10/2$	$\leq 0.05/54$ $\leq 0.10/6$	$\leq 0.05/63$ $\leq 0.10/20$	$\leq 0.05/55$ $\leq 0.10/46$

The characteristic crack width  $W_{rk}$  [mm] at a render strain value of 0.8%, determined with simple Method II pursuant to ETAG 004, cl. 5.5.4.1.

Table No. 15

Characteristic width of cracks $W_{rk}$ [mm] at render strain value of 0.8%		
	Warp direction	Weft direction
<b>R117 A101</b>	0.072	0.069

The width of cracks in reinforced base coat at 2% elongation is equal or lower than 0.15 mm.

## 3.4 Protection against noise (BWR 5)

### 3.4.1 Airborne sound insulation

No performance assessed.

## 3.5 Energy economy and heat retention (BWR 6)

### 3.5.1 Thermal resistance

The thermal transmittance of the substrate wall covered by the ETICS is calculated in accordance with the standard EN ISO 6946:

$$U_c = U + \chi_p \times n$$

Where:

$\chi_p \times n$  has only to be taken into account if it is greater than 0.04 W/(m<sup>2</sup>.K)

$U_c$  global (corrected) thermal transmittance of the covered wall (W/ (m<sup>2</sup>.K))

$n$  number of anchors (through insulation product) per 1 m<sup>2</sup>

$\chi_p$  local influence of thermal bridge caused by an anchor. The values listed below can be taken into account if not specified in the anchor's ETA:

= 0.002 W/K for anchors with a stainless steel screw covered by plastic anchors and for anchors with an air gap at the head of the screw

( $\chi_p \times n$  negligible for n < 20)

= 0.004 W/K for anchors with a galvanized steel screw with the head covered by a plastic material

( $\chi_p \times n$  negligible for n < 10)

= negligible for anchors with plastic nails (reinforced or not with glass fibres ...)

$U$  thermal transmittance of the current part of the covered wall (excluding thermal bridges) (W/ (m<sup>2</sup>.K)) determined as follows:

$$U_c = \frac{1}{R_i + R_{render} + R_{substrate} + R_{se} + R_{si}}$$

Where:

$R_i$  thermal resistance of the insulation product (according to declaration in reference to EN 13162) in (m<sup>2</sup>.K)/W

$R_{render}$  thermal resistance of the rendering system (about 0.02 in (m<sup>2</sup>.K)/W) or determined by test according to EN 12667 or EN 12664

$R_{substrate}$  thermal resistance of the substrate of the building (concrete, brick ...) in (m<sup>2</sup>.K)/W

$R_{se}$  external superficial thermal resistance in (m<sup>2</sup>.K)/W

$R_{si}$  internal superficial thermal resistance in ( $\text{m}^2 \cdot \text{K}$ )/W

The value of thermal resistance of each insulation product shall be given in the manufacturer's documentation along with the possible range of thicknesses. In addition, the point thermal conductivity of anchors shall be given when anchors are used in the ETICS.

### 3.6 Sustainable use of natural resources (BWR 7)

No performance assessed.

## 4 Assessment and verification of constancy of performance (hereinafter AVCP) system applied, with reference to its legal base

According to the European Commission decision 97/556/EC amended by the European Commission decision 2001/596/EC, the AVCP systems 1 and 2+ are valid (further described in Annex V to Regulation (EU) No. 305/2011).

Table No. 16

Product(s)	Intended use(s)	Level(s) or class(es) (Reaction to fire)	System(s)
External thermal insulation composite systems/kits (ETICS) with rendering	In external wall subject to fire regulations	A1 <sup>(1)</sup> , A2 <sup>(1)</sup> , B <sup>(1)</sup> , C <sup>(1)</sup>	1
		A1 <sup>(2)</sup> , A2 <sup>(2)</sup> , B <sup>(2)</sup> , C <sup>(2)</sup> , D, E, (A1 to E) <sup>(3)</sup> , F	2+
	In external wall not subject to fire regulations	Any	2+

- (1) Products/materials for which a clearly identifiable stage in the production process results in an improvement of the reaction to fire classification (e.g. an addition of fire retardants or a limiting of organic material)
- (2) Products/materials not covered by footnote (1)
- (3) Products/materials that do not require to be tested for reaction to fire (e.g. Products/materials of Classes A1 according to Commission Decision 96/603/EC)

## **5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD:**

In order to help the Notified Body to make an evaluation of conformity, the Technical Assessment Body issuing the ETA shall supply the information detailed below. This information together with the requirements given in EC Guidance Paper B will generally form the basis on which the factory production control (FPC) is assessed by the Notified Body.

This information shall initially be prepared or collected by the Technical Assessment Body and shall be agreed with the manufacturer. The following gives guidance on the type of information required:

1) ETA

Where confidentiality of information is required, this ETA makes reference to the manufacturer's technical documentation which contains such information.

2) Basic manufacturing process

The basic manufacturing process is described in sufficient detail to support the proposed FPC methods.

The different components of the ETICS are generally manufactured using conventional techniques. Any critical process or treatment of the components which affects performance are highlighted in the manufacturer's documentation.

3) Product and materials specifications

The manufacturer's documentation includes:

- detailed drawings (possibly including manufacturing tolerances),
- incoming (raw) materials specifications and declarations,
- references to European and/or international standards,
- technical data sheets.

4) Control Plan (as a part of FPC)

The manufacturer and the Technical and Test Institute for Construction Prague have agreed a Control Plan which is deposited with the Technical and Test Institute for Construction Prague in documentation which accompanies the ETA. The Control Plan specifies the type and frequency of checks/tests conducted during production and on the final product. This includes the checks conducted during manufacture on properties that cannot be inspected at a later stage and for checks on the final product.

Products not manufactured by the ETICS manufacturer shall also be tested according to the Control Plan. It must be demonstrated to the Notified Body that the FPC system contains elements securing that the ETICS manufacturer takes products conforming to the Control Plan from his supplier(s).

Where materials/components are not manufactured and tested by the supplier in accordance with agreed methods, then where appropriate they shall be subject to suitable checks/tests by the ETICS manufacturer referring to the Control Plan once again.

In cases where the provisions of the European Technical Assessment and its Control Plan are no longer fulfilled, the Notified Body shall withdraw the certificate and inform the Technical and Test Construction Institute Prague without delay.

Issued in Prague on 13/03/2017

by

**Ing. Mária Schaan**

Head of the Technical Assessment Body



**Annex No. 1 Insulation product characteristics for fully bonded ETICS with or without additional mechanical fixing – MW lamella (TR100)**

<b>Description and characteristics</b>	<b>Regulation</b>	<b>Declared characteristics MW lamella (TR100) (fibre orientation perpendicular)</b>	
		<b>Class, level according to EN 13162</b>	<b>Value</b>
Reaction to fire	EN 13501 -1+A1:2009	A1 or A2	Apparent density $\leq 160 \text{ kg/m}^3$
Thermal resistance	EN 12667 EN 12939	Defined in CE mark in accordance with EN 13162	
Thickness	EN 823	T5	-1 % or -1 mm*, +3 mm
		T4	-3 % or -3 mm*, +5 % or +5 mm**,
Length	EN 822	---	$\pm 2 \%$
Width		---	$\pm 1.5 \%$
Squareness	EN 824	---	$\leq 5 \text{ mm/m}$
Flatness	EN 825	---	$\leq 6 \text{ mm}$
Surface	ETAG 004	No additional treatment (homogenous, with coating)	
Dimensional stability under defined temperature and humidity	EN 1604	DS(70,90)	1 %
Water absorption	Short term water absorption	EN 1609	WS $\leq 1.0 \text{ kg/m}^2$
	Long term water absorption	EN 12087	WL(P) $\leq 3.0 \text{ kg/m}^2$
Diffusion factor ( $\mu$ )(-)	EN 12086 - EN 13162	MU1	1
Tensile strength perpendicular to the faces of insulation product in dry conditions	EN 1607	TR100	$\geq 100 \text{ kPa}$
Tensile strength perpendicular to the faces of insulation product in wet conditions	ETAG 004	---	$\geq 50 \text{ kPa}$
Shear strength	EN 12090	---	$\geq 20 \text{ kPa}$
Shear modulus of elasticity	EN 12090	---	$\geq 1000 \text{ kPa}$

\* higher value applies

\*\* lower value applies

Note: Classes and levels for individual characteristics comply with EN 13162+A1:2015

**Annex No. 2 Insulation product characteristics for fully bonded ETICS with or without additional mechanical fixing – MW lamella (TR80)**

<b>Description and characteristics</b>	<b>Regulation</b>	<b>Declared characteristics</b> <b>MW lamella (TR80)</b> (fibre orientation perpendicular)	
		<b>Class, level according to EN 13162</b>	<b>Value</b>
Reaction to fire	EN 13501-1 +A1:2009	A1 or A2	Apparent density ≤ 160 kg/m <sup>3</sup>
Thermal resistance	EN 12667 EN 12939	Defined in CE mark in accordance with EN 13162	
Thickness	EN 823	T5	-1 % or -1 mm*, +3 mm
		T4	-3 % or -3 mm*, +5 % or +5 mm**,
Length	EN 822	---	± 2 %
Width		---	± 1.5 %
Squareness	EN 824	---	≤ 5 mm/m
Flatness	EN 825	---	≤ 6 mm
Surface	ETAG 004	No additional treatment (homogenous, without coating)	
Dimensional stability under defined temperature and humidity	EN 1604	DS(70,90)	1 %
Water absorption	Short term water absorption	EN 1609	WS ≤ 1.0 kg/m <sup>2</sup>
	Long term water absorption	EN 12087	WL(P) ≤ 3.0 kg/m <sup>2</sup>
Diffusion factor ( $\mu$ )(-)	EN 12086 - EN 13162	MU1	1
Tensile strength perpendicular to the faces of insulation product in dry conditions	EN 1607	TR80	≥ 80 kPa
Tensile strength perpendicular to the faces of insulation product in wet conditions	ETAG 004	---	≥ 50 kPa
Shear strength	EN 12090	---	≥ 20 kPa
Shear modulus of elasticity	EN 12090	---	≥ 1000 kPa

\* higher value applies

\*\* lower value applies

Note: Classes and levels for individual characteristics comply with EN 13162+A1:2015

**Annex No. 3 Insulation product characteristics for mechanically fixed ETICS  
with anchors and supplementary bonding – MW board (TR15)**

<b>Description and characteristics</b>	<b>Regulation</b>	<b>Declared characteristics</b> <b>MW board (TR15)</b> (longitudinal fibre orientation)	
		<b>Class, level according to EN 13162</b>	<b>Value</b>
Reaction to fire	EN 13501 -1+A1:2009	A1 or A2	Apparent density $\leq 155 \text{ kg/m}^3$
Thermal resistance	EN 12667 EN 12939		Defined in CE mark in accordance with EN 13162
Thickness	EN 823	T5	-1 % or -1 mm*, +3 mm
		T4	-3 % or -3 mm*, +5 % or +5 mm**,
Length	EN 822	---	$\pm 2 \%$
Width		---	$\pm 1.5 \%$
Squareness	EN 824	---	$\leq 5 \text{ mm/m}$
Flatness	EN 825	---	$\leq 6 \text{ mm}$
Surface	ETAG 004	No additional treatment (homogenous, without coating)	
Dimensional stability under defined temperature and humidity	EN 1604	DS(70,90)	1 %
Water absorption	Short term water absorption	EN 1609	WS $\leq 1.0 \text{ kg/m}^2$
	Long term water absorption	EN 12087	WL(P) $\leq 3.0 \text{ kg/m}^2$
Diffusion factor ( $\mu$ )(-)	EN 12086 - EN 13162	MU1	1
Tensile strength perpendicular to the faces of insulation product in dry conditions	EN 1607	TR15	$\geq 15 \text{ kPa}$
Tensile strength perpendicular to the faces of insulation product in wet conditions	ETAG 004	---	$\geq 6 \text{ kPa}$
Shear strength	EN 12090	---	---
Shear modulus of elasticity	EN 12090	---	---

\* higher value applies

\*\* lower value applies

Note: Classes and levels for individual characteristics comply with EN 13162+A1:2015

**Annex No. 4 Insulation product characteristics for mechanically fixed ETICS  
with anchors and supplementary bonding – MW board  
RockSATE MD (TR10)**

<b>Description and characteristics</b>	<b>Regulation</b>	<b>Declared characteristics MW board RockSATE MD (TR10) (longitudinal fibre orientation)</b>	
		<b>Class, level according to EN 13162</b>	<b>Value</b>
Reaction to fire	EN 13501 -1+A1:2009	A1	Apparent density $\leq 155 \text{ kg/m}^3$
Thermal resistance	EN 12667 EN 12939	Defined in CE mark in accordance with EN 13162	
Thickness	EN 823	T5	-1 % or -1 mm*, +3 mm
Length	EN 822	---	$\pm 2 \%$
Width		---	$\pm 1.5 \%$
Squareness	EN 824	---	$\leq 5 \text{ mm/m}$
Flatness	EN 825	---	$\leq 6 \text{ mm}$
Surface	ETAG 004	No additional treatment (homogenous, without or with coating)	
Dimensional stability under defined temperature and humidity	EN 1604	DS(70,90)	1 %
Water absorption	Short term water absorption	WS	$\leq 1.0 \text{ kg/m}^2$
	Long term water absorption	WL(P)	$\leq 3.0 \text{ kg/m}^2$
Diffusion factor ( $\mu$ )(-)	EN 12086 - EN 13162	MU1	1
Tensile strength perpendicular to the faces of insulation product in dry conditions	EN 1607	TR10	$\geq 10 \text{ kPa}$
Tensile strength perpendicular to the faces of insulation product in wet conditions	ETAG 004	---	$\geq 4 \text{ kPa}$
Shear strength	EN 12090	---	---
Shear modulus of elasticity	EN 12090	---	---

\* higher value applies

Note: Classes and levels for individual characteristics comply with EN 13162+A1:2015

**Annex No. 5 Insulation product characteristics for mechanically fixed ETICS  
with anchors and supplementary bonding – MW board Panneau  
431 (TR10)**

<b>Description and characteristics</b>	<b>Regulation</b>	<b>Declared characteristics MW board Panneau 431 (TR10) (longitudinal fibre orientation)</b>	
		<b>Class, level according to EN 13162</b>	<b>Value</b>
Reaction to fire	EN 13501 -1+A1:2009	A1	Apparent density $\leq 155 \text{ kg/m}^3$
Thermal resistance	EN 12667 EN 12939	Defined in CE mark in accordance with EN 13162	
Thickness	EN 823	T5	-1 % or -1 mm*, +3 mm
Length	EN 822	---	$\pm 2 \%$
Width		---	$\pm 1.5 \%$
Squareness	EN 824	---	$\leq 5 \text{ mm/m}$
Flatness	EN 825	---	$\leq 6 \text{ mm}$
Surface	ETAG 004	No additional treatment (homogenous, without or with coating)	
Dimensional stability under defined temperature and humidity	EN 1604	DS(70,90)	1 %
Water absorption	Short term water absorption	WS	$\leq 1.0 \text{ kg/m}^2$
	Long term water absorption	WL(P)	$\leq 3.0 \text{ kg/m}^2$
Diffusion factor ( $\mu$ )(-)	EN 12086 - EN 13162	MU1	1
Tensile strength perpendicular to the faces of insulation product in dry conditions	EN 1607	TR10	$\geq 10 \text{ kPa}$
Tensile strength perpendicular to the faces of insulation product in wet conditions	ETAG 004	---	$\geq 4 \text{ kPa}$
Shear strength	EN 12090	---	---
Shear modulus of elasticity	EN 12090	---	---

\* higher value applies

Note: Classes and levels for individual characteristics comply with EN 13162+A1:2015

**Annex No. 6 Insulation product characteristics for mechanically fixed ETICS  
with anchors and supplementary bonding – MW boards  
ECOROCK MONO / RockSATE MD Plus (TR10)**

<b>Description and characteristics</b>	<b>Regulation</b>	<b>Declared characteristics MW boards ECOROCK MONO / RockSATE MD Plus (TR10) (longitudinal fibre orientation)</b>	
		<b>Class, level according to EN 13162</b>	<b>Value</b>
Reaction to fire	EN 13501 -1+A1:2009	A1	Apparent density $\leq 120 \text{ kg/m}^3$
Thermal resistance	EN 12667 EN 12939	Defined in CE mark in accordance with EN 13162	
Thickness	EN 823	T5	-1 % or -1 mm*, +3 mm
Length	EN 822	---	$\pm 2 \%$
Width		---	$\pm 1.5 \%$
Squareness	EN 824	---	$\leq 5 \text{ mm/m}$
Flatness	EN 825	---	$\leq 6 \text{ mm}$
Surface	ETAG 004	No additional treatment (homogenous, without or with coating)	
Dimensional stability under defined temperature and humidity	EN 1604	DS(70,90)	1 %
Water absorption	Short term water absorption	WS	$\leq 1.0 \text{ kg/m}^2$
	Long term water absorption	WL(P)	$\leq 3.0 \text{ kg/m}^2$
Diffusion factor ( $\mu$ )(-)	EN 12086 - EN 13162	MU1	1
Tensile strength perpendicular to the faces of insulation product in dry conditions	EN 1607	TR10	$\geq 10 \text{ kPa}$
Tensile strength perpendicular to the faces of insulation product in wet conditions	ETAG 004	---	$\geq 4 \text{ kPa}$
Shear strength	EN 12090	---	---
Shear modulus of elasticity	EN 12090	---	---

\* higher value applies

Note: Classes and levels for individual characteristics comply with EN 13162+A1:2015

**Annex No. 7 Insulation product characteristics for mechanically fixed ETICS with anchors and supplementary bonding – MW board Frontrock Max E (TR10)**

<b>Description and characteristics</b>	<b>Regulation</b>	<b>Declared characteristics MW board Frontrock Max E (TR10) (dual density board, longitudinal fibre orientation)</b>	
		<b>Class, level according to EN 13162</b>	<b>Value</b>
Reaction to fire	EN 13501 -1+A1:2009	A1	Apparent density $\leq 155 \text{ kg/m}^3$
Thermal resistance	EN 12667 EN 12939	Defined in CE mark in accordance with EN 13162	
Thickness	EN 823	T5	-1 % or -1 mm*, +3 mm
Length	EN 822	---	$\pm 2 \%$
Width		---	$\pm 1.5 \%$
Squareness	EN 824	---	$\leq 5 \text{ mm/m}$
Flatness	EN 825	---	$\leq 6 \text{ mm}$
Surface	ETAG 004	No additional treatment (homogenous, without or with coating)	
Dimensional stability under defined temperature and humidity	EN 1604	DS(70,90)	1 %
Water absorption	Short term water absorption	WS	$\leq 1.0 \text{ kg/m}^2$
	Long term water absorption	WL(P)	$\leq 3.0 \text{ kg/m}^2$
Diffusion factor ( $\mu$ )(-)	EN 12086 - EN 13162	MU1	1
Tensile strength perpendicular to the faces of insulation product in dry conditions	EN 1607	TR10	$\geq 10 \text{ kPa}$
		TR7.5**	$\geq 7.5 \text{ kPa}^{**}$
Tensile strength perpendicular to the faces of insulation product in wet conditions	ETAG 004	---	$\geq 4 \text{ kPa}$
			$\geq 3 \text{ kPa}^{**}$
Shear strength	EN 12090	---	---
Shear modulus of elasticity	EN 12090	---	---

\* higher value applies

\*\* valid only if insulation product's thickness is 60 mm

Note: Classes and levels for individual characteristics comply with EN 13162+A1:2015

**Annex No. 8 Insulation product characteristics for mechanically fixed ETICS with anchors and supplementary bonding – MW board External Wall DD Panel (TR10)**

<b>Description and characteristics</b>	<b>Regulation</b>	<b>Declared characteristics</b> <b>MW board External Wall DD Panel (TR10)</b> (dual density board, longitudinal fibre orientation)	
		<b>Class, level according to EN 13162</b>	<b>Value</b>
Reaction to fire	EN 13501 -1+A1:2009	A1	Apparent density $\leq 155 \text{ kg/m}^3$
Thermal resistance	EN 12667 EN 12939		Defined in CE mark in accordance with EN 13162
Thickness	EN 823	T5	-1 % or -1 mm*, +3 mm
Length	EN 822	---	$\pm 2 \%$
Width		---	$\pm 1.5 \%$
Squareness	EN 824	---	$\leq 5 \text{ mm/m}$
Flatness	EN 825	---	$\leq 6 \text{ mm}$
Surface	ETAG 004	No additional treatment (homogenous, without or with coating)	
Dimensional stability under defined temperature and humidity	EN 1604	DS(70,90)	1 %
Water absorption	Short term water absorption	EN 1609	$\leq 1.0 \text{ kg/m}^2$
	Long term water absorption	EN 12087	$\leq 3.0 \text{ kg/m}^2$
Diffusion factor ( $\mu$ )(-)	EN 12086 - EN 13162	MU1	1
Tensile strength perpendicular to the faces of insulation product in dry conditions	EN 1607	TR10	$\geq 10 \text{ kPa}$
Tensile strength perpendicular to the faces of insulation product in wet conditions	ETAG 004	---	$\geq 4 \text{ kPa}$
Shear strength	EN 12090	---	---
Shear modulus of elasticity	EN 12090	---	---

\* higher value applies

Note: Classes and levels for individual characteristics comply with EN 13162+A1:2015

**Annex No. 9 Anchors, description of individual product characteristics contained in the ETA**

Trade name	Plate diameter (mm)	Characteristic pull-out resistance	Plate stiffness (kN/mm)	Load at plate rupture (kN)
<b>Surface assembly</b>				
<b>Ejotherm STR U, STR U 2G</b>	60	see ETA - 04/0023	0.60	2.08
<b>EJOT SDM-T plus</b>	60	see ETA - 04/0064	0.60	2.08
<b>EJOT H1 eco</b>	60	see ETA - 11/0192	0.60	1.40
<b>BRAVOLL PTH-KZ 60/8-La</b>	60	see ETA – 05/0055	0.70	2.10
<b>BRAVOLL PTH-S 60/8-La</b>	60	see ETA - 08/0267	0.90	2.60
<b>BRAVOLL PTH-EX</b>	60	see ETA - 13/0951	0.60	1.40
<b>KEW TSD 8</b>	60	see ETA - 04/0030	0.53	1.63
<b>KEW TSD-V</b>	60	see ETA - 08/0315	1.20	1.75
<b>KEW TSDL-V</b>	60	see ETA – 12/0148	1.20	1.75
<b>KOELNER TFIIX-8M</b>	60	see ETA - 07/0336	1.00	1.75
<b>Koelner KI-10M</b>	60	see ETA - 07/0291	0.45	0.85
<b>Koelner KI-10N, KI-10NS</b>	60	see ETA - 07/0221	0.50	1.23
<b>KOELNER TFIIX-8S</b>	60	See ETA - 11/0144	0.60	2.04
<b>KOELNER TFIIX-8P</b>	60	See ETA - 13/0845	0.30	1.38
<b>Hilti HTS-P</b>	60	See ETA - 14/0400	0.60	1.60
<b>Hilti SX-FV</b>	60	See ETA - 03/0005	0.70	1.73
<b>Hilti-Dämmstoff-Befestigungselement XI-FV</b>	60	See ETA - 03/0004	0.40	1.60
<b>Hilti WDVS-Schraubdübel D-FV. D-FV T</b>	60	See ETA - 05/0039	0.80	1.93
<b>fischer Schlagdübel TERMOFIX CF 8</b>	60	See ETA - 07/0287	0.50	1.65
<b>fischer TERMOZ 8U</b>	60	See ETA - 02/0019	0.50	2.45
<b>fischer Schlagdübel TERMOZ 8N</b>	60	See ETA - 03/0019	0.50	1.34
<b>fischer Schlagdübel TERMOZ 8 NZ</b>	60	See ETA - 03/0019	0.50	1.43
<b>fischer TERMOZ CS 8</b>	60	See ETA - 14/0372	0.60	1.70
<b>Wkret-met LMX ø 10</b>	60	see ETA - 08/0172	0.50	1.64

Trade name	Plate diameter (mm)	Characteristic pull-out resistance	Plate stiffness (kN/mm)	Load at plate rupture (kN)
<b>Wkret-met LMX ø 8</b>	60	see ETA - 09/0001	0.50	1.53
<b>Wkret-met LFM ø 10</b>	60	see ETA – 06/0105	0.5	2.4
<b>Wkret-met LFM ø 8</b>	60	see ETA – 06/0080	0.5	1.26
<b>Wkret-met WKTHERM ø 8</b>	60	see ETA - 11/0232	0.60	4.3
<b>Wkret-met WKTHERM S</b>	60	see ETA - 13/0724	0.60	4.3
<b>AMEX LDK</b>	60	see ETA - 09/0182	0,40	0,53
<b>Countersunk assembly</b>				
<b>Ejotherm STR U, STR U 2G</b>	60	see ETA - 04/0023	0.60	2.08
<b>BRAVOLL PTH-S 60/8-La</b>	60	see ETA - 08/0267	0.90	2.60
<b>KOELNER TFIX-8ST</b>	60	see ETA - 11/0144	0.60	2.04
<b>fischer TERMOZ 8 SV</b>	60	see ETA - 06/0180	1.10	2.13
<b>Wkret-met eco drive</b>	60 (110)	see ETA – 13/0107	0.60	2.80
<b>Slip-on plates</b>				
<b>BRAVOLL IT PTH</b>	100, 140	see ETA - 06/0267		
<b>EJOT VT, VT 2G</b>	90	see ETA – 04/0023		
<b>EJOT SBL 140 plus</b>	140	see ETA – 04/0023		
<b>KEW DSB</b>	90, 100, 140	see ETA – 04/0030		
<b>Koelner KWL</b>	90, 100, 140	see ETA – 07/0221		
<b>Fischer DT</b>	90, 100, 140	see ETA – 02/0019		
<b>Kret-met TDX, TDX-P</b>	90, 140	see ETA – 05/0225		
<b>AMEX TK</b>	140	see ETA – 09/0182		
<b>Hilti HDT-FV-9</b>	90	see ETA – 14/0400		

**In addition to this list, anchors assessed in accordance with ETAG 014 can be used provided that such anchors meet the following requirements:**

Requirements		
Plate diameter	$\geq 60 \text{ mm}$	
Plate stiffness	Surface assembly:	$\geq 0.3 \text{ kN/mm}$
	Countersunk assembly:	$\geq 0.6 \text{ kN/mm}$
Rupture force of anchor's plate	$\geq$ Higher of figures $R_{\text{panel}}$ and $R_{\text{joint}}$ in relevant table in Cl. 3.3.5	
Nail of anchor	Made out of metal	

## Annex No. 10 Description of glass fibre mesh

	Description	Strength after ageing	
		Absolute strength after ageing (N/mm)	Relative residual strength after ageing, of the strength in the as- delivered state (%)
<b>R117 A101</b>	4,5 x 4,0 mm	$\geq 20$	$\geq 50$
<b>R 131 A101</b>	3,8 x 3,8 mm		
<b>SSA-1363-145</b>	4 x 5,5 mm		
<b>SSA-1363-160</b>	4 x 5 mm		
<b>LIFITEX PRO 145</b>	4 x 5,5 mm		
<b>LIFITEX PRO 165</b>	4 x 4 mm		
<b>AKE 145</b>	4,0 x 4,5 mm		
<b>AKE 170/160</b>	3,8 x 3,8 mm		
<b>Halico A 150</b>	4,7 x 4,5 m		
<b>OPTIMA-NET 150</b>	4,0 x 4,5 mm		
<b>OPTIMA-NET 150</b>	3,6 x 4,0 mm		
<b>MASTERNET CLASSIC 145</b>	5,0 x 5,0 mm		
<b>LAKMA TERM A 150</b>	4,7 x 4,5 mm		